



Product Information

BD CLASSIC 3100 Antimicrobial

100% Epoxy Floor Coating

Description

BDC 3100 AM is a two component, 100% solids, high-build, low viscosity, low odor, cyclo-aliphatic, chemical resistant epoxy with antimicrobial additives. This epoxy topcoat comes in clear and a variety of pigmented colors. The antimicrobial additives are used to cease mildew and algae growth in this 2-part epoxy in accordance with ASTM D5590-00 and Algae Resistance Test 1.3.Alg.1.

Uses

BDC 3100 AM epoxy is used to create industrial seamless floors in manufacturing plants, mechanical rooms, warehouses, commercial kitchens, and residential garages. In combination with color quartz or paint chips it can be used to create a decorative floor coating. BDC 3100 AM epoxy (with aggregate) can also be used as a mortar for overlays or repairs for concrete. 3100 AM clear is an excellent high build concrete sealer for interior use over many other types of coatings such Texture Crete or over acid stained floors. 3100 AM can be applied directly to the concrete without a special primer.

Advantages

- Low Viscosity
- Meets USDA criteria
- 100% Solids
- Chemical Resistant
- High Strength
- Water Clear or Pigmented
- Durable yet Flexible
- Low Odor
- High-Build
- Superior Adhesion

Coverage

Coverage will vary depending on condition of surface and desired thickness.

As a Primer:

300-400 sf per gallon after thinning 10% with acetone.

As a Coating:

100-300 sf per gallon

For Epoxy Mortar:

1 gallon of epoxy mixed with 5 gallons of sand will yield approximately 3 to 4 gallons of mortar.

Packaging

- 1 1/2 gallon kits
- 15 gallon kits

Colors

Clear, Travatan, Cape Cod Grey, Deep Tan, Pewter Grey,

White, Black and Tile Red

Inspection

Concrete must be clean, dry, and free of grease, paint, oil, dust, curing agents, or any foreign material that will prevent proper adhesion. The concrete should be at least 2500 psi and feel like 30-grit sandpaper. The concrete should be porous and be able to absorb water. A minimum of 28 days cured is required on all concrete. Before starting flooring work, test existing concrete slab for efflorescence, moisture, and hydrostatic pressure.

Surface Preparation

Over Concrete Surfaces: Shotblasting is the preferred method for preparing the concrete. In some cases you may prepare by acid etching, floor scrubbing with a nylogrit brush and waterblasting to achieve a clean and uniform surface that feels like 50 grit sandpaper. If acid etching is done, be sure to properly etch and then adequately neutralize by scrubbing and rinsing several times followed by power washing. Prepare the surface so that the product will soak in and properly bond.

Over existing Epoxy: Sand the surface with a floor buffer and 50 grit sand paper, remove debris and wipe with denatured alcohol just before new application.

Mixing

As a Coating: Premix each component separately. Mix 2 parts A with 1 part B, by volume, into a clean container. Mix thoroughly with a low speed (400-600 rpm) drill motor for 3-4 minutes. Make sure to scrap the sides and bottom of the container during mixing. The product may be thinned with acetone in which case it must be applied thinly enough to allow solvent to escape (minimum 300 sf per gallon). After mixing is completed, remove from container within 5 minutes as epoxy will begin to generate heat. Spread immediately onto the floor, as product is spread out you will have longer working time (10-15 minutes at 70 degrees).

For an Epoxy Mortar: Mix 2 to 5 parts of a washed and kiln dried aggregate, by volume, to 1 part of mixed BDC 3100 AM and mix until uniform in consistency.

Application

Primer: Prime the surface using BDC 1200 (thinned with 10% acetone), 11 series or 14 series (thinned with water). Read individual product information sheets. The 3100 AM may also be used as a primer when thinned 10% with acetone. Primer coat should be applied thinly and worked into the surface to help seal avoid pin holes.

As a Coating: Apply BDC 3100 AM within 24 hours after the primer coat. Immediately after mixing, spread a strip of the batch onto the surface along the edges where it will be "cut in" using a brush. Pour the remaining material near the "cut in" area and spread evenly using a

trowel or squeegee and back roll using a 1/4" nap non-shedding roller. A notched trowel or squeegee will help regulate the thickness and a porcupine roller will help to release trapped air and minimize bubbles. Depending on the look, thickness, chemical and abrasion resistance desired, 1 to 2 coats may be applied. A non-skid surface can be achieved by broadcasting and/or back rolling a washed and kiln dried aggregate into the coating.

For an epoxy mortar: Prime the area with a neat (no sand added) batch of BDC 1200, 11 series or 14 series primer. Within 24 hours, apply the prepared mortar using a trowel.

- Do not apply over concrete under hydrostatic pressure.
- For interior use only unless protected by an UV resistant coating.
- Concrete must be cured for a minimum of 28 days.
- Solvents added to thin such as acetone will make product combustible or flammable in which case be aware of sparks or open flame.
- If solvent is added, the products must be applied thinly to allow the solvent to escape or proper curing will occur.

Limitations

- Do not apply at temperatures below 50°F or above 95°F.
- After mixing completely (3-4 minutes remove from mixing container and apply to floor)

Clean Up

Uncured material can be removed with a solvent. Cured material can only be removed mechanically.

Technical Data for Clear

Viscosity (ASTM-D-445-83, Brookfield, RVTD, Sprindle 4)	1030 cps
Gel time (Techne GT-4 Gelation Timer)	55 (150 mass/min)
Tensile Strength (ASTM-D-638-86)	7,250 psi
Tensile Modulus	385,000 psi
Tensile Elongation (ASTM-D-638-86)	5.5 %
Heat Deflection at 264 psi (ASTM-D-648) *	47 C
Shore D Hardness (ASTM-D-2240-86) *	81
Abrasion Resistance @ 1000 cycles Wt. Loss (gms)	0.0041
Mar Resistance (ASTM-D-5178-91)	1.30 kg
Pencil Hardness	2H
Impact, inches-lbs Direct/Reverse	14/1
Glass Transition Temperature (ASTM-D-3418-82)	124 F
Color (ASTM-D-1544-80)	>1 Gardner
Thin Film Set Times at 70 F (BK Drying Recorder)	6 hrs.
Flexural Strength (ASTM-D-790-88)	12,185psi
Flexural Modulus	445,00 psi
Cross Hatch Adhesion (0-Worst, 5-Best)	4
Compressive Strength @ yield (ASTM 695-85)	11,550psi
Compressive Modulus (ASTM 695-85)	370,000 psi
Glass Transition	46C
Chemical Composition	Modified Bisphenol A epoxy resin crosslinked with aliphatic and cycloaliphatic polyamines
VOC	0 g/l

*Properties determined after 7 days cure at 25 C°

REAGENT	Initial Hard.		After 3 hrs		After 24 hrs		After 3 days		After 7 days		After 28 days		After 90 days	
	% wt.	Hard	% wt.	Hard	% wt.	Hard	% wt.	Hard	% wt.	Hard	% wt.	Hard	% wt.	Hard
10% Acetic Acid	82	0.7	80	2.1	72	4.01	69	6.13	62	10.15	63	15.4	46	
10% Lactic Acid	82	0.38	80	1.19	79	2.31	78	3.48	77	5.71	74	8.78	59	
Toluene	82	0.06	80	0.81	75	3.07	65	6.89	52	20.3	46	18.32	52	
Xylene	82	0.01	78	0.04	77	0.36	75	1.29	70	4.65	72	15.39	57	
Trichloroethane	82	0.05	77	0.4	77	2.31	74	3.54	68	13.74	65	-	-	
Methanol	82	3.13	66	8.37	38	12.83	25	6.23	30	5.71	35	-	-	
Ethanol	82	0.99	75	2.89	63	5.55	46	8.55	45	9.34	43	6.81	52	
Butyl Cellosolve	82	0.37	76	1.47	73	3.83	66	6.34	63	12.42	53	-	-	
Methyl Ethyl Ketone	82	6.41	63					DESTROYED						
Skydrol	82	0.11	77	0.46	77	1.26	74	2.18	74	3.67	75	6.03	56	
70% Sulfuric Acid	82	0.22	83	0.11	82	0.15	81	0.21	81	0.16	81	-0.16	81	
98% Sulfuric Acid	82	-15.6	80					DESTROYED						
Deionized Water	82	0.07	82	0.31	81	0.54	82	0.93	82	1.65	80	2.14	80	
50% Sodium Hydroxide	82	0.06	82	-0.05	82	-0.04	82	-0.03	83	-0.06	83	-0.1	63	
Bleach	82	0.09	83	0.28	83	0.52	83	0.83	82	1.28	81	1.67	72	